

## Kapileen 150 black

### Description:

Coextruded 3 layer film (Silage cover film). Total opacity to sunlight & Very good oxygen barrier

Property	Test method	Unit	General Data and Value
Thickness	DIN 53370	µm	150
Dart-Drop plain	ASTM D1709	g	300
Tensile at break MD TD	ASTM D882	MPa MPa	23 22
Elongation at break MD TD	ASTM D882	% %	450 500
Elmendorf tear resistance MD TD	ASTM D1922	g/µ g/µ	4 10
Min/max ambient temperature		°C	-50 / 85

*md = machine direction, td = transversal direction*

- Lifetime:** Guaranteed 18 months in Benelux, Germany and Northern France.
- Attention:** Special attention should be paid to the positioning of fork-lift as the film directly on top of the pallet is vulnerable to local pressure build-ups and may tear if not handled with care. Special attention should also be paid when opening the packaging, as incidental cutting of straps may cause rolls to fall of the pallet.
- Storage:** The product must be stored indoors and must be used within 3 years after delivery.
- Use:** Brokers Kunststoffen B.V. will not be liable to claims or restitutions when the product is used in combination with too high a concentration of chlorine or sulphur. Pesticides may contain substances that may affect the specification of our products. Please contact our customer service for questions.
- Disposal:** The product should be disposed of in an environmental friendly way.
- Complaints:** In case of a complaint, please contact our customer service.