

Underlayer film (> 8m)

Description:

Coextruded 3 layer PE-film (Silage cover film). User-friendly (thin and extra light in weight) – Extra protection – Prevents air accumulating between the silage film and the fodder – Increases fodder quality.

Property		Test method	Unit	General Data and Value
Thickness		DIN 53370	µm	T40
Dart-Drop	plain	ASTM D1709	g	225
Tensile at break	MD TD	ASTM D882	MPa MPa	25 26
Elongation at break	MD TD	ASTM D882	% %	300 500
Elmendorf tear resistance	MD TD	ASTM D1922	g/µ g/µ	6 20
Min/max ambient temperature			°C	-50 / 85

md = machine direction, td = transversal direction